

DERWENT-ACC-NO: 2001-563486

DERWENT-WEEK: 200255

COPYRIGHT 2006 DERWENT INFORMATION LTD

TITLE: Method for manufacturing valve spring for engine having  
high fatigue resistance

INVENTOR: KIM, T H; LEE, B H ; PARK, S E ; PARK, S U

PATENT-ASSIGNEE: DAE WON KANG UP CO LTD[DAEWN] , DAE WON STEEL  
JH[DAEWN]

PRIORITY-DATA: 1999KR-0037071 (September 2, 1999)

PATENT-FAMILY:

PUB-NO	PUB-DATE	LANGUAGE	PAGES	MAIN-IPC
KR 2001025964 A	April 6, 2001	N/A	001	C21D 009/02
KR 323468 B	February 6, 2002	N/A	000	C21D 009/02

APPLICATION-DATA:

PUB-NO	APPL-DESCRIPTOR	APPL-NO	APPL-DATE
KR2001025964A	N/A	1999KR-0037071	September 2, 1999
KR 323468B	N/A	1999KR-0037071	September 2, 1999
KR 323468B	Previous Publ.	KR2001025964	N/A

INT-CL (IPC): C21D009/02

ABSTRACTED-PUB-NO: KR2001025964A

BASIC-ABSTRACT:

NOVELTY - A method for manufacturing a valve spring for an engine is provided to manufacture a valve spring which is more durable under a high stress compared with an existing valve spring by changing the conventional manufacturing process to increase a fatigue life of a valve spring, thereby forming residual compression stress inside a coil.

DETAILED DESCRIPTION - The method for manufacturing a valve spring for an engine comprises the processes of a quenching process in which the spring material is heated at a temperature of 850 deg.C for 10 minutes, cooled in a salt bath having a temperature of 320 deg.C for 90 seconds before cooling and air cooling, tempering the coil at a temperature of 350 to 450 deg.C for 30 minutes after coiling the material in the state that a fresh raw material is not heat treated, polishing and shot peening the coil, and tempering and setting the coil so that a residual compression stress layer formed at over 0.2

mm depth from surface of the coil thereby improving fatigue resistance of a valve spring.

CHOSEN-DRAWING: Dwg.1/10

TITLE-TERMS: METHOD MANUFACTURE VALVE SPRING ENGINE HIGH FATIGUE RESISTANCE

DERWENT-CLASS: M24

CPI-CODES: M24-D02A;

SECONDARY-ACC-NO:

CPI Secondary Accession Numbers: C2001-167179